

TECHNICAL DATA SHEET

Parameters	Unit Measure	Methods	Limits
Diameter	mm		8,00-10,00
Length	mm		<50,00
Bulk weight	kg/m		<600,00
Granules with size less than 5 mm	%		<10,00
Fines < 3 mm	%	SS 18 71 80	<1,50
Moisture	%	SS 18 71 70	<12,00
Bark	%		
Ash	%	SS 18 71 71	<1,50
Volatile matter	%	SS-ISO 562	
Gross calorific value	kcal/kg	SS 18 71 72	>4900
Net calorific value	kcal/kg	SS 18 71 72	>4100
Durability	%	prCEN/TS 15210-1	
Initial deformation temp.	deg. C	ASTM D 1857-03	
Sulphur	%	SS 18 71 77	<0,08

